

Seal 341®

HILLYARD
FLOOR CARE

Seal and finish. Formulated to enhance the rich, natural colors of your hard floors without leaving a plastic-looking surface. It also seals resilient tile floors to create a smooth, unbroken base for high speed finishes. Seal 341 is versatile enough to be used as a top coat on resilient floors. Seal 341 not only enhances the natural colors in hard floors, it protects all floors from dirt, spills, and abrasions that come from heavy traffic.

Features & Benefits

- Formulated to seal porous flooring.
- Easy to apply no matter what the conditions.
- Attractive, low lustre finish.

Directions

NEW HARD FLOORS: Allow new hard floor surfaces to set 30 days to ensure proper curing of Portland terrazzo or grout joints. Scrub floor with HILLYARD RENOVATOR. Pick up scrubbing solution with wet vac, autoscrubber, or mop; flood rinse with HILLYARD NUTRA-RINSE solution. Pick up solution, damp mop rinse with water, and allow floor to dry for at least one hour. For older hard floors, follow these same procedures, but increase RENOVATOR dilution per label directions to remove heavy wax and polish buildup. Use HILLYARD ASSAULT or DEVASTATOR for extremely heavy buildup or areas inaccessible to floor machines.

NEW RESILIENT FLOORS: After newly installed resilient flooring is laid and the adhesive has dried at least two weeks, scrub with a solution of HILLYARD POWER-STRIP or DEVASTATOR, following label directions to remove factory finishes. Pick up scrubbing solution with wet vac, autoscrubber, or mop; flood rinse with HILLYARD NUTRA-RINSE solution. Pick up solution, damp mop rinse with water, and allow floor to dry for at least one hour. For older resilient floors, follow these same procedures, but increase the dilution rate of POWER-STRIP or DEVASTATOR to remove heavy wax or polish buildup.

SYNTHETIC SPORTS FLOORS: Check with the flooring manufacturer's warranty regarding the use of maintenance products before proceeding. Once the warranty expires, or you elect to coat the floor, remove any previous polishes or waxes using HILLYARD SALVATION following label directions. Thoroughly rinse the floor and allow it to dry one hour before proceeding. Apply SEAL 341 and maintain the floor following the directions listed below. Do not use solvents or aggressive strippers to maintain or strip synthetic sports flooring.

APPLICATION: Apply SEAL 341 with a clean synthetic mop to clean, dry floor. Under normal conditions, apply up to three coats allowing 30 minutes between coats. Temperature, humidity, and air circulation affect curing times. For resilient flooring, you can use Seal 341 as a top coat, or top coat with your choice of a quality Hillyard polish.

NOTICE: Keep container closed when not in use. Do not pour unused material back into container. Maintain adequate ventilation and floor temperatures above 60 deg.F (16 deg.C) during use.

High Speed Burnishing: Because high speed burnishing is affected by many variables, including equipment type, pad pressure, frequency of burnishing, and traffic loads contact Hillyard Technical Service for pad recommendations.

Certifications, Registrations & Notes

Classified by Underwriters Laboratories, Inc.® as to slip resistance. (1865).



Safety

See material safety data sheet and product label for safety information, handling and proper use.

HMIS

	Concentrate
Health	0
Flammability	0
Reactivity	0

Technical Specifications

Color	White
Scent	Non-Objectionable
Appearance	Milky Emulsion
pH (concentrate)	8.50 - 9.50
Non-Volatile Matter	22.00%
Dilution Rate	RTU

Availability

Item	Pack
HIL0034106	4 - 1 Gallon Containers
HIL0034107	1 - 5 Gallon Bag-In-Box
HIL0034109	1 - 55 Gallon Drum

Coverage Rates: 1,500 - 2,000 Sq. Ft. per Gallon
Rates can vary greatly based on surface and application method.

HILLYARD

P.O. Box 909
St. Joseph, MO 64502
1-800-365-1555
www.hillyard.com